

Stopray

Product Specification: Stopray utilize by IGU / Double Glazing 6-12-6, (with 100% air), Coating position #2

Type	Colour	Light Performances			Energy Performances						U Value		
		EN			EN	ISO	NFRC	EN	ISO	NFRC	EN	ISO	NFRC
		LT (%)	LR Out (%)	LR In (%)	SF (%)	SHGC (%)	SC			W/(m ² .K)		U-Summer W/(m ² .K)	
Stopray Vision 60T ⁽³⁾	Neutral	59	14	20	0.37	0.35	N/A	0.43	0.40	N/A	1.5	N/A	N/A
Stopray Vision 60	Neutral	60	15	18	0.35	0.33	N/A	0.40	0.38	N/A	1.5	N/A	N/A
Stopray Vision 50T ⁽³⁾	Neutral	49	17	21	0.31	0.29	N/A	0.36	0.33	N/A	1.5	N/A	N/A
Stopray Vision 50	Neutral	50	19	22	0.29	0.27	N/A	0.33	0.31	N/A	1.5	N/A	N/A
Stopray Smart 51/33 ⁽⁴⁾	Neutral	50	25	17	0.33	0.32	N/A	0.38	0.37	N/A	1.6	N/A	N/A
Stopray Smart 30/20 ⁽⁴⁾	Neutral Bluish	29	28	15	0.21	0.21	N/A	0.24	0.24	N/A	1.6	N/A	N/A
Stopray Ace 42T ⁽³⁾	Neutral Greyish	41	16	12	0.25	0.25	N/A	0.29	0.29	N/A	1.6	N/A	N/A

Remark :

- The data are calculated using spectral measurements that are conforming to standards EN 410, ISO 9050 (1990)
- The U-value is calculated according to standard EN 673.
- This coating must be tempered to reach its final performances.
- Stopray Smart can be used in tempered or non-tempered versions. Due to its high absorption factor (EA = 53%), we recommend always tempering Stopray Smart 30/20. Specifications, technical and other data are based on information available at the time of preparation of this document and are subjected to change without notice. AGC cannot be held responsible for any deviation between the data introduced and the conditions on site.